

MF.bio

ergonomico indeformabile



MATERIALI MF.BIO®



MF. BIO® schiuma viscoelastica di nuova generazione, formulata con un contenuto parziale di materie prime rinnovabili (oli vegetali).

MF. BIO® new generation viscoelastic foam, formulated with a partial content of renewable raw materials (vegetable oils).

MF. BIO® espuma viscoelástica de nueva generación, formulada con un contenido parcial de materias primas renovables (aceites vegetales).

MF. BIO® viskoelastischer schaum der neuen generation, formuliert mit einem teilweisen anteil an erneuerbaren rohstoffen (pflanzliche öle).

MF. BIO® mousse viscoélastique de nouvelle génération, formulée avec une teneur partielle en matières premières renouvelables (huiles végétales).

BLOCCO DA STAMPO

	COLORE COLOUR COLORES COLORIS FARBE	LARGHEZZA WIDTH ANCHURA LARGEUR BREITE	ALTEZZA HEIGHT ALTURA HAUTEUR HÖHE	UNI EN ISO 845 ISO 1855 DENSITÀ DENSITY PESO ESPECÍFICO POIDS SPECIFIQUE RAUMGEWICHT	UNI EN ISO 3386-1 ISO 3386 PORTANZA COMPRESSIVE HARDNESS DUREZA PORTANCE STAUCHHÄRTE	UNI EN ISO 2439-B UNI 6353 SFORZO PRESSIONE PRESSURE STRESS ESFUERZO A LA PRESIÓN EFFORT DE PRESSION EINDRUCKHÄRTE	ISO 1798 ALLUNGAMENTO ELONGATION AT BREAK ESTIRAMIENTO ALLONGEMENT DEHNUNG	UNI EN ISO 1856 DEFORMAZIONE PERM. COMPRESSION SET DEFORMACIÓN PERM. DEFORMATION PERM. VERFORMUNG
		cm	cm	Kg/m ³	Kpa	N	%	%
MF BIO	VE	190/200	30	40	1,7/1,9	70/80	150	5